

ImagePerfect™ 2406 Plus Photogloss Paper

ImagePerfect™ 2406 Plus Photogloss Paper is a high gloss paper that is intended for indoor applications only. It meets the requirements of ISO 14001 and it has been specially created for digital printing on large-format inkjet printers and is suitable for printing with eco solvent and solvent inks as well as UV-cured and latex inks.

ImagePerfect™ 2406 Photogloss Paper is the leading option in photo-quality printing for all high-end, commercial posters, point-of-sale applications, counter-top displays, promotional campaigns, etc; all with a high-gloss finish. It offers sharp images and high print definition due to its large colour gamut and high black value. This paper meets the requirements of ISO 14001 and it can be validated, therefore, as being sustainable, environmentally-friendly and ecologically produced, with the production of the wood that is used in the production of the paper being a socially and environmentally responsible process. Laminate: IP 2810-101, IP 2830-200, IP 2840-106

Printing recommendations: Be aware that paper is sensitive to heat and humidity and it will tend, therefore, to show buckling much faster than some other types of media. Buckling may occur when the material is left to sit on the heater plate without printing. In such cases, before printing is resumed, please perform a media feed in order to move the potential buckles away from the danger zone, thereby avoiding printhead strikes. Laminate: IP 2810-101, IP 2830-200, 2840-106.

Specifications	
Description	Photogloss paper
Colour	White gloss
Thickness	245mym
Weight	260g/m ²
Temperature Range	N/A
Durability (unprinted)	N/A
Shelf Life	2 years, 20°C / 50% humidity

© May 2022 Eikon Ltd. Technical specifications are subject to change without prior notice. All trademarks mentioned are the property of their respective owners

For more information about ImagePerfect please visit www.imageperfect.com

Eikon Ltd, 38 Port Royal Avenue, Lune Industrial Estate, Lancaster. United Kingdom

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of such products for their specific use, including, but not limited to, the application, conditions, maintenance, and the Purchaser shall assume all risk and liability of every nature in connection therewith. All technical data are subject to change without prior notice. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

Eikon gives no express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of fitness for any particular use and/or non-infringement. All products are sold subject to Eikon's general terms and conditions of sale. Eikon's aggregate liability, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoiced to Purchaser in respect of any occurrence or series of occurrences. In the event of improper use and/or incorrect processing that does not comply with our instructions, any and all liability is excluded. In no circumstances shall Eikon be liable for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.