

ImagePerfect™ 2508

Clear Gloss Cast Vinyl (FR)

ImagePerfect™ 2508 is a clear gloss cast vinyl incorporating a repositionable, permanent, solvent-based adhesive. This material meets the highest durability requirements and is the first-choice product for vehicle wraps and many other 3D applications. It has been specially created for digital printing on large-format inkjet printers and is suitable for printing with eco solvent and solvent inks as well as UV-cured and latex inks.

ImagePerfect™ 2508 Clear Gloss Cast Vinyl is a premium cast vinyl that is intended for indoor and long-term outdoor applications, such as markings and decorations, vehicle graphics, complete vehicle wraps and many other 3D applications. It features non-migrating plasticizers and UV stabilizers, thereby ensuring long-term outdoor durability. It promotes high levels of print quality with remarkable text definition and a large colour gamut to ensure colourful images with vibrant area in-fills. It is equipped with a backing paper that offers excellent lay flat properties. Laminate: IP 2800-100, IP 2800-200, IP 2830-109.

Attention: Please make sure the printed IP 2508 is completely dry before laminating and applying. Before the IP 2508 is applied, the surface should be completely cleaned. The use of IP Surface Cleaner (MIP1000) and the lint-free, IP Surface Cleaning Cloths (MMS8373) is a good match component cleaning solution to ensure that the surface is dry and free of dust and grease. The use of acetone as an additional surface cleaner is also recommended, particularly in the case of low-energy surfaces, such as coated car glass, or on any complex body shapes (incorporating concave surfaces). When the material has been applied into convex or concave contours and is thereby subject to deformation, it is then imperative that post-heating is carried out. As such, heat up the vinyl evenly over the contours at a temperature of 100°C. For best results, use an infrared thermometer for accuracy (MIPIR361).

Specifications	
Description	Cast vinyl
Colour	Clear gloss
Thickness	50mym
Weight	N/A
Adhesive	Solvent based acrylic, permanent
Adhesive Strength	18N/25mm (Finat TM 1/24h)
Release Paper	PE-coated silicone paper, 140g/m ²
Temperature Range	-30°C to +90°C
Durability (unprinted)	8 years
Flame Retardancy	B1
Shelf Life	2 years, 20°C / 50% humidity

© May 2022 Eikon Ltd. Technical specifications are subject to change without prior notice. All trademarks mentioned are the property of their respective owners.

For more information about ImagePerfect please visit www.imageperfect.com

Eikon Ltd, 38 Port Royal Avenue, Lune Industrial Estate, Lancaster. United Kingdom

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of such products for their specific use, including, but not limited to, the application, conditions, maintenance, and the Purchaser shall assume all risk and liability of every nature in connection therewith. All technical data are subject to change without prior notice. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

Eikon gives no express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of fitness for any particular use and/or non-infringement. All products are sold subject to Eikon's general terms and conditions of sale. Eikon's aggregate liability, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoiced to Purchaser in respect of any occurrence or series of occurrences. In the event of improper use and/or incorrect processing that does not comply with our instructions, any and all liability is excluded. In no circumstances shall Eikon be liable for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.