

TEST REPORT

No. : XMIN2206005910CM

Date : Jun 20, 2022

Page: 1 of 7

CUSTOMER NAME: EIKON LTD
ADDRESS: 38 PORT ROYAL AVENUE, LUNE INDUSTRIAL ESTATE,
LANCASTER, UNITED KINGDOM

Sample Name : STREETAPP
Product Specification : IP2555
Material and Mark : PVC Adhesive Vinyl

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : SDFS2206003522FF
Date of Receipt : Jun 01, 2022
Testing Start Date : Jun 01, 2022
Testing End Date : Jun 20, 2022
Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services Co., Ltd Xiamen Branch
Testing Center

Civi Huang
Authorized signatory

TEST REPORT

No. : XMIN2206005910CM

Date : Jun 20, 2022

Page: 2 of 7

Test Result Summary

Test(s) Requested	Result(s)
EN 13501-1:2018 Fire classification of construction products and building elements-Part 1: Classification using data from reaction to fire tests	Classification: B-s2, d0
Summary:	
1. For further details, please refer to the following page(s).	

TEST REPORT

No. : XMIN2206005910CM

Date : Jun 20, 2022

Page: 3 of 7

TESTS AND RESULTS

Test Conducted:

This test is conducted as per EN 13501-1:2018 Fire classification of construction products and building elements-Part 1: Classification using data from reaction to fire tests. And the test methods as following:

1. EN 13823:2020 Reaction to fire tests for building products-Building products excluding floorings exposed to the thermal attack by a single burning item.
2. EN ISO 11925-2:2020 Reaction to fire tests-Ignitability of building products subjected to direct impingement of flame-Part 2: Single-flame source test.

Mounting and fixing (For EN 13823:2020):

Test sample is installed on the substrate by glue (test substrates is calcium silicate board meets the requirement of EN13501-1 of Class A2-s1,d0, the density of 900 kg/m³ and thickness of 10mm. Use glue brand: RUBSTIK; Applying the amount: About 200g/m²).

Test Results:

Test method	Parameter	Number of tests	Results
EN 13823:2020	FIGRA _{0.2MJ} (W/s)	3	60.6
	FIGRA _{0.4MJ} (W/s)		6.6
	THR _{600s} (MJ)		0.7
	SMOGRA (m ² /s ²)		118.2
	TSP _{600s} (m ²)		11.1
	LFS < edge of specimen (Yes/No)		Yes
	Flaming particles or droplets within 600s (Yes/No); Combustion time, if any burning time: (≤10s / >10s)		No
EN ISO 11925-2:2020 Exposure = 30 s	F _s ≤ 150 mm (Yes/No)	12	Yes
	Ignition of the filter paper		No

Remark:

FIGRA-Fire growth rate index used for classification purposes [W/s]

For the classes A2 and B, FIGRA_{0.2MJ}

For the classes C and D, FIGRA_{0.4MJ}

LFS-Lateral flame spread [m]

THR_{600s}-Total heat release within 600 s [MJ]

SMOGRA-Smoke growth rate [m²/s²]

TSP_{600s}-Total smoke production within 600 s [m²]

Classification and direct field of application:

This classification has been carried out in accordance with EN 13501-1:2018.

TEST REPORT

No. : XMIN2206005910CM

Date : Jun 20, 2022

Page: 4 of 7

Classification:

Fire behaviour		Smoke production			Flaming droplets	
B	—	s	2	,	d	0

Remark:

The classes with their corresponding fire performance are given in Table 1.

Reaction to fire classification is based on the 7-step scale of A1 to F, where A1 is the highest level and F is the lowest level.

Statement:

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Warning:

This classification report does not represent type approval or certification of the product.

The test laboratory has, therefore, play no part in sampling the product for the test, although it holds appropriate references to the manufacturer's factory production control that is aimed to be relevant to the samples tested and that will provide for their traceability.

TEST REPORT

No. : XMIN2206005910CM

Date : Jun 20, 2022

Page: 5 of 7

Table 1 — Classes of reaction to fire performance for construction products excluding floorings and linear pipe thermal insulation products.

Class	Test method(s)		Classification criteria	Additional classification
A1	EN ISO 1182 ^a and		$\Delta T \leq 30^{\circ}\text{C}$, and $\Delta m \leq 50\%$, and $t_f=0$ (i.e. no sustained flaming)	-
	EN ISO 1716		$PCS \leq 2.0\text{MJ/kg}$ ^a and $PCS \leq 2.0\text{MJ/kg}$ ^{b c} and $PCS \leq 1.4\text{MJ/m}^2$ ^d and $PCS \leq 2.0\text{MJ/kg}$ ^e	-
A2	EN ISO 1182 ^a or	and	$\Delta T \leq 50^{\circ}\text{C}$, and $\Delta m \leq 50\%$, and $t_f \leq 20\text{ s}$	-
	EN ISO 1716		$PCS \leq 3.0\text{MJ/kg}$ ^a and $PCS \leq 4.0\text{MJ/m}^2$ ^b and $PCS \leq 4.0\text{MJ/m}^2$ ^d and $PCS \leq 3.0\text{MJ/kg}$ ^e	-
	EN 13823		$FIGRA \leq 120\text{W/s}$ and $LFS < \text{edge of specimen}$ and $THR_{600s} \leq 7.5\text{MJ}$	Smoke production ^f and Flaming droplets/particles ^g
B	EN 13823 and	$FIGRA \leq 120\text{W/s}$ and $LFS < \text{edge of specimen}$ and $THR_{600s} \leq 7.5\text{MJ}$	Smoke production ^f and Flaming droplets/particles ^g	
	EN ISO 11925-2 ⁱ Exposure =30s	$F_s \leq 150\text{mm}$ within 60 s		
C	EN 13823 and	$FIGRA \leq 250\text{W/s}$ and $LFS < \text{edge of specimen}$ and $THR_{600s} \leq 15\text{MJ}$	Smoke production ^f and Flaming droplets/particles ^g	
	EN ISO 11925-2 ⁱ Exposure=30s	$F_s \leq 150\text{mm}$ within 60 s		

TEST REPORT

No. : XMIN2206005910CM

Date : Jun 20, 2022

Page: 6 of 7

Class	Test method(s)	Classification criteria	Additional classification
D	EN 13823 and	FIGRA \leq 750W/s	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ Exposure=30s	Fs \leq 150mm within 60 s	
E	EN ISO 11925-2 ⁱ Exposure =15s	Fs \leq 150mm within 20 s	flaming droplets/particles ^h
F	EN ISO 11925-2 ⁱ Exposure =15s	Fs>150mm within 20 s	-

^a For homogeneous products and substantial components of non-homogeneous products.

^b For any external non-substantial component of non-homogeneous products.

^c Alternatively, any external non-substantial component having a PCS \leq 2,0 MJ/m², provided that the product satisfies the following criteria of EN 13823: FIGRA \leq 20 W/s, and LFS < edge of specimen, and THR_{600s} \leq 4,0 MJ, and s1, and d0.

^d For any internal non-substantial component of non-homogeneous products.

^e For the product as a whole.

^f In the last phase of the development of the test procedure, modifications of the smoke measurement system have been introduced, the effect of which needs further investigation. This may result in a modification of the limit values and/or parameters for the evaluation of the smoke production.

s1 = SMOGRA \leq 30m²/s² and TSP_{600s} \leq 50m²; s2 = SMOGRA \leq 180m²/s² and TSP_{600s} \leq 200m²;
s3 = not s1 or s2

^g d0 = No flaming droplets/ particles in EN 13823 within 600 s;

d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s;

d2 = not d0 or d1.

Ignition of the paper in EN ISO 11925-2 results in a d2 classification.

^h Pass = no ignition of the paper (no classification);

Fail = ignition of the paper (d2 classification).

ⁱ Under conditions of surface flame attack and, if appropriate to the end-use application of the product, edge flame attack.

Note: The above test project/method was carried out by subcontractors.

TEST REPORT

No. : XMIN2206005910CM

Date : Jun 20, 2022

Page: 7 of 7

SAMPLE INFORMATION AND PICTURES

Thickness of the test specimen: 0.35mm
Density of the test specimen: 208g/m²



Before Test (EN 13823)



After Test (EN 13823)

***** End of report*****