

Indicative test report

No. 2019-1019

issued 29.01.2019

Applicant:

Spandex AG
Aegertweg 4

D – 8305 Dietlikon
Schweiz

Date of order:

05.11.2018

Date of sampling:

**no official taking out of the sample from a
representative of the Warringtonfire Frankfurt GmbH**

Date of arrival:

20.12.2018

Date of test:

15.01.2019

Order

Testing of the flammability (building class B1) according to DIN 4102-1 (May 1998)

Description / designation of the test object

Product name: IP 2830-205 Matt UV Print Laminate

Description of the relevant test procedure

DIN 4102 part 1 (May 1998)

1. Description of the test material

1.1 Details of the customer:

Product name: IP 2830-205 Matt UV Print Laminate

Product description:

Tradename: IP 2830-205
Sample material: self adhesive vinyl
Material type: PVC
Production technique: Calandred
Total Thickness: 70 μ
Area weight: N/A
Colour: Clear

Intended end use of the product: Self-adhesive films application

1.2 By Warringtonfire Frankfurt GmbH determined values:

Self adhesive

colour: clear
thickness: 0,08 mm
square weight: 107 g/m²

Testing after clima storage at 23° C and 50 % rel. hum. L. moisture

2. Test results

2.1 “Brandschacht” test according to DIN 4102-1

Specimen A: Sample in direction of production

Test results of the “Brandschacht” tests part 1						
line no.		measurements test sample				
			A	B	C	D
1	<u>sample arrangement according to DIN 4102 Part 15, section 5.4 Table No. 1</u>		1			
2	<u>flame height max. over lower sample edge</u> time ¹⁾	Cm	60			
		min : s	01:26			
3	<u>ascertainties on the front side</u> Flaming/glowing time ¹⁾	min : s	01:16			
4	<u>melting / burning through</u> time ¹⁾	min : s	no			
5	<u>ascertainties on the back side</u> Flaming/glowing time ¹⁾	min : s	no			
		6	discolouring time ¹⁾	min : s	no	
7	<u>burning droplets</u> begin ¹⁾	min : s	no			
8	extent					
8	occasional dripping of material		no			
9	constant dripping of material					
10	<u>separating from burning sample parts</u> begin ¹⁾	min : s	no			
		11	occasional separating parts			
		12	constant separating parts			
13	duration of burning on the sieve tray (max.)	min : s	no			
14	influence on the burner flame by dripping of / separating material time ¹⁾	min : s	no			
		15	<u>earlier end of test</u> end of the fire scenario on the sample ¹⁾	min : s	no	
16	time of a possible resulted test stop ¹⁾	min : s				

¹⁾ time from start of test

Test results of the "Brandschacht" tests part 2						
line no.		Measurements test sample				
			A	B	C	D
17	<u>flaming after end of test</u> duration	min : s	no			
18	number of sample		no			
19	front side of sample		no			
20	backside of sample		no			
21	flame length		cm	--/--		
22	<u>glowing after end of test</u> duration	min . s	--/--			
23	number of sample		no			
	place of occurrence		no			
24	lower sample part		no			
25	upper sample part		no			
26	front side of sample		no			
27	backside of sample					
28	<u>smoke density</u> < 400 % x min		0			
29	> 440 % x min		--/--			
30	<u>diagram in annex no.</u>		1			
31	<u>residual length</u> single results	cm	35 / 36 38 / 34			
32	average of the single results	cm	35			
33	foto of the sample on page		5			
34	<u>smoke temperature</u> max. of the average results	°C	116			
35	time ¹⁾	min : s	09:52			
36	<u>diagram in annex no.</u>		1			

¹⁾ time from start of test

Remarks: none

2.2 Appearance of the specimen after the test:

Sample A



3. Indicative Assessment

The determined results showed that the material is able to fulfill the requirements for the B1 classification according to DIN 4102-1 (May 1998).

4. Special note

The materials were not tested after an outside storage.

In combination with other materials (for example coatings, deposits) the burning behaviour could be influenced unfavourable so that the classification above is not valid any longer. According to DIN 4102-1 the burning behaviour in combination with other materials has to be tested separately.

Frankfurt, the 29.01.2019

H. Anders
Tester in charge

P. Scheinkönig
Prüfstellenleiter Bau PVO



The results of the tests relate only to the behaviour of the test sample which is designated on the top.

Test reports are only allowed to be published or reproduced, not changed in form and tenor without permission of the Warringtonfire, Frankfurt GmbH

The abridged account of a test report is only allowed with the agreement of the von Warringtonfire, Frankfurt GmbH

This test report is a translation of the German version 2019-1019 (issued 29.01.2019). In case of doubt only the German version is valid

This test report contains 6 pages and 1 annex.

Annex 1 to the test report No. 2019-1019 issued 29.01.2019

Sample A:

